

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Hideyuki ONO et al.

Serial No: 10/594,784

Filed: September 29, 2006

For: ACRYLIC ELASTOMER
COMPOSITION

Attorney Docket No.: 14056-11

Examiner: Karuna Reddy

Group Art Unit: 1796

Conf. No.: 7107

SUPPLEMENTAL RESPONSE

Further to applicants' Preliminary Amendment filed December 20, 2010, applicants note that the Table provided on page 11 inadvertently listed "ML" in the last line rather than "MH."

The corrected Table is provided as follows:

Table

	Experiment				
	EX. 2	1	2	3	4
Formulation					
Acrylic rubber	100	100	100	100	100
FEF carbon black	55	55	55	55	55
Stearic acid	1	1	1	1	1
4,4'-bis(α,α' -dimethylbenzyl)-diphenylamine	2	2	2	2	2
Phosphoric acid ester-based processing aid	1	1	1	1	1
4,4'-diaminodiphenyl ether	1				